

Avesta Pickling Paste 101

100% Stainless

The original pickling paste

Avesta Pickling Paste 101 is the original and only real paste on the market with over 50 years experience. It offers a perfect paste consistency that gives good adhesion to difficult surfaces and reduces the risk of splashing.

Standard applications


This paste is universal and specifically intended for standard brush pickling of weld seams and smaller surfaces of all stainless steel grades.

Features

- Restores damaged stainless steel surfaces, such as weld seams, by removing weld oxides, the underlying chromium-depleted layer and other defects that may cause local corrosion.
- Improved pickling result, offers a brighter surface with less discolouration than classical products.
- Offers a perfect paste consistency that gives good adhesion to difficult surfaces and reduces the risk of splashing.
- No risk of sagging thanks to its thick paste consistency.
- Heat sensitive, only for storing and pickling in temperature range of +10 to 30 °C.
- For non-heavy-duty applications we suggest our low fuming Avesta BlueOne™ Pickling Paste 130 in order to improve the environmental impact and safety when pickling.




Avesta Pickling Paste 101 – the only real paste on the market.



Before and after pickling. Avesta Pickling Paste 101 – for brush pickling in all positions.

Instructions for use



1. Stir or shake the paste before use.
2. Apply the paste with an acid-resistant brush.
3. Leave the paste to work 30 min to 4 hours (depending on temperature and steel grade). The temperature of the workpiece should always be higher than +5 °C.
4. Remove pickling residues by using a high-pressure water jet, or with a stainless steel brush and then rinse with water. The waste water should be treated before discharge.

Packaging

Avesta Pickling Paste 101 is supplied in a 2,6 kg polyethylene container supplied in a 4-pack cardboard box.

All packing material follows the UN regulations for Hazardous goods.

Storage

Avesta Pickling Paste 101 should be stored indoors at room temperature. Containers must be kept properly closed, in an upright position and inaccessible to unauthorised persons.

The product is perishable and should not be kept in storage longer than necessary. It has a maximum shelf life of two years when stored at room temperature. Exposure to higher temperatures (> 35 °C) may damage the product and reduce the shelf life.

Worker safety

Avesta First Aid Spray 910 should be readily accessible to all those who work with pickling. It comes in a handy 200 ml spray can and the content has been optimised to decontaminate small acid-splashes of pickling paste.

Protective clothing. In general users should wear acid-resistant overalls, gloves and rubber boots. Face visor should be used and, if necessary, suitable respiratory protective devices.

Special conditions may apply from one country to another. Consult our website where updated Safety Data Sheets can be found.

Waste treatment

The waste water produced when pickling contains acids and should be treated with Avesta Neutraliser 502 or with slaked lime to a pH-value of 7–10 before discharge.

Heavy metals from the stainless steel are precipitated as a sludge, and should be sent for deposition according to local regulations.

Empty containers (HDPE) must be cleaned and can then be recycled according to local regulations.

Other information

For more information, please visit our website www.avestafinishing.com where you can find Safety Data Sheets and other useful information.

Böhler Welding Group Nordic AB

Avesta Finishing Chemicals
Lodgatan 14
SE-211 24 Malmö, Sweden
Tel: +46 (0)40 28 83 00
Fax: +46 (0)40 93 94 24
www.avestafinishing.com



Avesta
Finishing Chemicals